




Imaging

Images do not accurately portray size or color.

Accu-Vu™ Imaging:



Comments:

This diagram is an example and does not represent the actual facet arrangement of the item described

General Report Comments:

Document No: 1112660 Validation Date: 16 February 2021

Identification

Mineral Type: Natural Corundum Transparency: Transparent
 Variety: Sapphire Color Description: Blue

Carat Weight: Not Determined Shape: Marquise
 Measurements: Approx. 16.5 x 7.85 x 6.59 mm Cutting Style: Mixed Cut

Comments: Set in a white metal ring with two trapezoidal and two round diamonds (identified at random).

Identification

American Gemological Laboratories™
 America's first and most highly respected origin lab.

Founded in 1977,

AGL is an internationally recognized gemstone testing facility, specializing in comprehensive colored stone analyses.

AGL has the distinction of being the first laboratory in the United States to issue Country-of-Origin reports. Our company and its principals have a long tradition of research into the detection of and reporting on gem identification-and-classification, gemstone treatments and provenance determinations.

Our staff is composed of experts in the field of gemstone testing and reporting. Our findings reflect the latest knowledge and analytical techniques to ensure the highest standards are applied on every stone we test.

AGL's testing and reporting methodology provide you with unsurpassed quality and reliability. We are committed to providing the highest level of service and reporting that our clients and the industry have come to expect from the AGL.

Origin

Provenance: Ceylon (Sri Lanka)

Comments: Based on available gemological information, it is the opinion of the Laboratory that the origin of this material would be classified as Ceylon (Sri Lanka).



Origin

Enhancement

Standard: No gemological evidence of heat Additional: Clarity enhancement: None

Comments: Non-heated sapphires are scarce. Sapphires are commonly heated to modify their color and appearance.

Enhancement

| | | | | | | | | | | | | | | | |
|-----------|-----------|------|------|------|----------------|-----------|------|----------|--------|-------------|---------------|-------|----------|--------|-----------|
| 1 | 2 | 3 | 4 | 5 | 6 | 7 | 8 | 9 | 10 | None | Insignificant | Minor | Moderate | Strong | Prominent |
| Excellent | Very Good | Good | Fair | Poor | Extremely Rare | Very Rare | Rare | Uncommon | Common | Very Common | | | | | |

Enhancement Stability Index™

Degree of Clarity Enhancement & Relative Rarity™

M. Chaipaksa
 Monruedee Chaipaksa, Senior Gemologist

Christopher P. Smith
 Christopher P. Smith, President

